



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> C08L 59/00 // (C08L 59/00, 83:04, 51:06) (C08L 59/00, 83:04, 23:08) (C08L 59/00, 83:04, 51:06, 25:08) (C08L 59/00, 83:04, 23:08, 25:08)	<b>A1</b>	<b>(11) International Publication Number:</b> WO 96/28510  <b>(43) International Publication Date:</b> 19 September 1996 (19.09.96)
<b>(21) International Application Number:</b> PCT/US96/03429  <b>(22) International Filing Date:</b> 13 March 1996 (13.03.96)  <b>(30) Priority Data:</b> 7/52347 13 March 1995 (13.03.95) JP  <b>(71) Applicant (for all designated States except US):</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> SHINOHARA, Kenichi [JP/JP]; Eda-Higashi 4-6-19, Inoue Terrace House, Tsuzuki- ku, Yokohama-shi, Kanagawa 224 (JP).  <b>(74) Agent:</b> WALKER, P., Michael; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> CA, CN, KR, SG, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> POLYACETAL RESIN COMPOSITION AND MOLDED ARTICLE THEREOF  <b>(57) Abstract</b>  An objective of the invention is to provide a polyacetal resin composition which has excellent resistance to heat aging and grease resistance, has welded sections with no decrease in physical properties, and has improved friction characteristics, and molded articles therefrom. A polyacetal resin composition comprising per 100 parts by weight of a polyacetal resin, 2-7 parts by weight of a polymer composition based on an olefinic polymer having glycidyl-group-containing pendant chains and 0.5-2.5 parts by weight of a dimethyl siloxane polymer of a plasticity of at least one; a polyacetal resin composition further comprising 100 parts by weight of the preceding resin composition along with 0.05-0.5 parts by weight of carbon black; and molded articles therefrom.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

# TITLE

## **POLYACETAL RESIN COMPOSITION AND MOLDED ARTICLE THEREOF**

### 5 FIELD OF THE INVENTION

The present invention relates to a polyacetal resin composition, specifically to a resin composition materially comprising a polyacetal resin, a polymer composition based on an olefinic polymer having glycidyl-group-containing pendent chains and a dimethyl siloxane polymer; and this resin composition containing, in addition, carbon black. The invention also relates to a molded article, obtained by molding these resin compositions, having excellent resistance to heat aging and grease resistance, and no loss in physical properties in molded sections, along with improved abrasion resistance characteristics.

### DESCRIPTION OF THE RELATED ART

Polyacetal resins, which are plastic materials with excellent repeated fatigue characteristics and wear resistance and well balanced mechanical properties, are used in a broad area, such as in automobiles and electrical and electronic parts, and the like. However, polyacetal resin, in general, tends to oxidatively degrade at high temperatures with mechanical properties decreasing too rapidly to be maintained when subjected to repeated usage at the high temperatures of 90-120°C.

Many proposals have been made for improving resistance to heat aging (long term heat stability) which, for example, includes methods of adding antioxidants and heat stabilizers, such as polyamides and polydicarboimide as disclosed in U.S. Patents 4,098,843 and 4,845,161. Japanese Patent Laid Open H4-345649 discloses a polyacetal resin composition with improved resistance to heat aging and grease resistance (long term oil resistance) comprising a polyacetal resin and a compound having epoxy, nitrile groups and/or oxazolyl groups as functional groups.

The present inventors developed and proposed (Japanese Patent Application Publication H6-111711), an improved polyacetal resin composition which has resistance to heat aging and grease resistance and

has welded sections with no decrease in physical properties, which materially comprises a polyacetal resin, an olefinic type polymer having glycidyl-group-containing pendent chains, and a styrene polymer having an oxazolyl-group-containing pendent chains.

5

#### Problems to be Solved by the Invention

Much improvement has been made on polyacetal resins as described above. Molded articles using these improved polyacetal resin compositions, such as molded gears, switches, rollers, switch mechanism parts, cams, and the like, which are subjected to high loads, sometimes in their service suffer from problems of wear or squeaking problems, for which further improvement has been required on wear resistance, or the like, friction characteristics.

15

It is an objective of this invention to provide a polyacetal resin composition which has excellent resistance to heat aging and grease resistance and has welded sections with no decrease in physical properties, along with further improved friction characteristics of the polyacetal resin.

20

### SUMMARY OF THE INVENTION

This invention relates to a polyacetal resin composition having per 100 parts by weight of a polyacetal resin, 2-7 parts by weight of a polymer composition based on an olefinic polymer having glycidyl-group-containing pendant chains and 0.5-2.5 parts by weight of a dimethyl siloxane polymer of a plasticity of at least one, as well as molding articles made from the resin composition.

30

### BRIEF DESCRIPTION OF THE DRAWING

Figure 1 is a schematic diagram for the reciprocating friction wear tester used in the friction characteristic evaluation test.

35

### DETAILED DESCRIPTION

The means for solving the problems in the prior art are as follows.

The present inventors discovered that the addition of a dimethyl siloxane polymer to a polyacetal resin composition materially comprising a polyacetal resin, an olefin type polymer having glycidyl containing  
5 pendent chains, and a styrene polymer having oxazolyl-group-containing pendent chains, considerably improves wear resistance, and that an additional incorporation of carbon black substantially decreases the wear rate.

10 The present invention is a polyester resin composition comprising per 100 parts by weight of a polyacetal resin, 2-7 parts by weight of a polymer composition based on an olefinic polymer having glycidyl-group-containing pendent chains and 0.5-2.5 parts by weight of a  
15 dimethyl siloxane polymer of a plasticity of at least one, as well as molded articles therefrom.

Specifically, the present invention is a resin composition in which, in the above composition,

20 (a) the polymer composition is a resin composition of a single olefinic polymer having glycidyl-group-containing pendent chains;

(b) the polymer composition is a melt blend of 100 parts by weight of an olefinic polymer having glycidyl-group-containing pendent chains  
25 and 50-200 parts by weight of a styrene polymer having an oxazolyl group.

(c) a resin composition obtained by adding 0.05-5 parts by weight of carbon black per 100 parts by weight of the above resin compositions  
30 (a) and (b);

and molded articles of each of the preceding resin compositions (a), (b), and (c).

35 The resin compositions of this invention may use common polyacetal resins as the polyacetal resin component, such as homopolymers or their copolymers of an aldehyde, such as formaldehyde, a cyclic oligomer of formaldehyde, such as trioxane,

tetraoxane, or the like, or copolymers of these aldehydes with cyclic ethers or acetals, such as ethylene oxide, propylene oxide, 1,3-dioxolane, or the like.

5           These polyacetal resins mainly are polymers having main chains of repeating units represented by  $-(CH_2O)_n-$  ( $n$  represents a positive number) and/or  $-(CHR-O)_n-$  (where  $R$  is an alkyl group;  $n$  is a positive number) having termini which are not protected or are protected with protecting groups such as  $-OCH_3$ ,  $-OCF_3$ ,  $-OCH_2OH$ , having number  
10           average molecular weights of 10,000 - 100,000, preferably 20,000-70,000.

          A melt blend is used as a polymer composition based on an olefinic polymer having glycidyl-group-containing pendent chains in the resin composition of this invention which is either an olefin polymer  
15           having glycidyl-group-containing pendent chains or a melt blend of this olefinic polymer and a styrene polymer having an oxazolyl group.

          Olefinic polymers having glycidyl-group-containing pendent chains include, for example, random ethylene/glycidyl(meth)acrylate  
20           copolymers, random ethylene-methyl(meta)acryl-glycidyl(meth)acrylate terpolymers, random ethylene-butyl(meth)acrylate-glycidyl(meth)acrylate terpolymers, random ethylene-vinylacetate-glycidyl(meth)acrylate terpolymers, and the like, either singly or in a mixture of two or more, without being limited to these examples.

25           Silane polymers having oxazolyl groups are, for example, copolymers of 2-vinyl-oxazoline and styrene, which can be readily manufactured via a well known radical copolymerization reaction.

30           Incorporating a polymer composition into the polyacetal resin improves the resistance to heat aging and grease resistance of its molded articles, but use of a melt blend, particularly of an olefinic polymer having glycidyl-group-containing pendent chains and a styrene polymer containing an oxazolyl group, further improves resistance to heat aging  
35           than is possible with single use of an olefinic polymer having glycidyl-group-containing pendent chains. Too small an amount of the polymer composition incorporated will fail to give a sufficient improvement effect on resistance to high temperature heat aging and grease resistance, while

too large an amount will adversely affect the high strength and high modulus, which are the inherent mechanical properties of the polyacetal resin molded article. The preferred amount compounded is 2-7 parts by weight per 100 parts by weight of the polyacetal resin.

5

If the polymer composition used is a melt blend of an olefinic polymer having glycidyl-group-containing pendent chains and a styrene polymer with oxazolyl groups, use is made of a melt blend comprising 100 parts by weight of an olefinic polymer having glycidyl-group-  
10 containing pendent chains and 50-200 parts by weight of a styrene polymer having an oxazolyl group. If the amount of the styrene polymer having oxazoyle groups is too small, olefinic polymer particles having glycidyl-group-containing pendent chains can no longer be incorporated into the styrene polymer having an oxazolyl group, and instead will be  
15 present by themselves in the polyacetal resin, which will not only decrease considerably the welding strength of the molded article, but also will cause crack formation due to nonuniform dispersion. On the other hand, if the amount of styrene polymer having an oxazolyl group is in too high an amount, there will be no synergistic operation of the the heat  
20 stabilizing effect by a styrene polymer having an oxazolyl group and a heat stabilizing effect by an olefinic polymer having a glycidyl group, thus failing to improve sufficiently the heat aging resistance.

The resin composition of this invention uses a dimethyl siloxane  
25 polymer which has a plasticity as measured by a Williams' Plastometer of 1.0 or higher, preferably 1.4-1.9. Too low a plasticity means that the composition during the melt kneading of the resin composition or during molding will show a phenomenon of slipping on the screw surface in a kneader or molding machine, which makes it difficult to fill a specific  
30 amount into the mold. These dimethyl siloxane polymers, in general, have extremely high polymer viscosities, for which it is difficult to express as the viscosity of a conventional silicone oil, being a polymer having a far higher viscosity than the viscosity of 150,000 cs of the silicone polymers which are conventionally used as lubricants. The  
35 average DPC molecular weights are about 550,000 to 700,000.

The dimethyl siloxane polymer improves the wear resistance of the molded articles, but if the amount compounded is too small, no

satisfactory improvement is obtained on the wear resistance of the molded articles; while if the amount is too high, it not only adversely affects the moldability, but it also decreases the wear resistance of the molded articles.

5

The suitable amount of the dimethyl siloxane polymer to be incorporated is 0.5-2.5 parts by weight per 100 parts by weight of the polyacetal resin.

10

Incorporating carbon black into the above resin composition of this invention gives a resin composition with further improved moldability and wear resistance of the molded article. A suitable amount of carbon black incorporated is 0.05-0.5 parts by weight per 100 parts by weight of each resin composition. If the amount of the carbon black compound is too small, there is no significant effect on improving the the wear resistance of the molded article; while if it is too high an amount, this not only causes an adverse affect on moldability due to nonuniform dispersion or thermal degradation, but it also decreases the mechanical properties of the molded articles, particularly their impact resistance, along with a reduction in their wear resistance.

15

20

Each resin composition of this invention, within the range of not adversely affecting its inherent properties, may be mixed with a variety of additives which are normally added to the polyacetal resin, for example, an antioxidant, a heat stabilizer, a formaldehyde trap, a UV absorber, a coloring pigment, a mold release, a lubricant, or the like.

25

A resin composition based on a polyacetal resin of this invention can be readily prepared by a known method, for example, by mixing well each of these components followed by melt kneading using a single screw or twin screw extruder, or the like, thereby preparing pellets.

30

If a melt blend is used as the polymer composition comprising an olefinic polymer having glycidyl-group-containing pendent chains and a styrene polymer having an oxazolyl group, it is preferred to prepare pellets by a method similar to the above from a melt blend of an olefinic polymer having glycidyl-group-containing pendent chains and a styrene polymer having an oxazolyl group followed by melt-kneading again the

35



resultant pellets with other components. Use of this method allows the styrene polymer having an oxazolyl group to incorporate the olefin polymer having glycidyl pendent chains, forming a core-shell structure with a high probability.

5

The various resin pellets of this invention may be used to prepare, by molding by the usual methods, molded articles that have resistance to heat aging and grease resistance, and that have welding sections with minimal decrease in physical properties and excellent wear resistance.

10

## EXAMPLES

### (1) Preparation of Resin Compositions

15

#### a) Components Used for Polyacetal Resin

Polyacetal homopolymer standard resin (tradename Delrin 500 PNC 10, manufactured by the Dupont Company).

20

#### Polymer Composition:

A: Random ethylene-glycidyl methacrylate-N-butylacrylate terpolymer (monomer content: 5% glycidyl methacrylate and 30% N-butylacrylate, manufactured by the DuPont Company).

25

B: A polymethyl methacrylate (PMM) grafted copolymer of an ethylene/glycidyl methacrylate copolymer (EGMA) (monomer content: glycidyl methacrylate 10.5%, EGMA/PMMA = 70/30; tradename: Modibar [Phonetic Translation] 4200, manufactured by Nippon Yushi K.K.).

30

C: A random copolymer of 2-vinyl oxazoline (monomer content: 5%) and styrene (tradename: Epicross RPS-005, manufactured by Nippon Shokubai K.K.).

35

D: Pellets obtained by mixing 60 parts of polymer composition A and 40 parts by weight of C, followed by melt kneading at barrel a

temperature of 190°C using a conventional extruder, followed by water cooling and cutting.

Silicone Gum Concentrate: Polyacetal resin (tradename: Delrin DE8100 HBNC100, manufactured by the DuPont Company) was fed to a twin screw extruder, melt kneaded at a resin temperature of 190-210°C, followed by adding at the rate of 40 parts by weight, with respect to 100 parts by weight of polyacetal resin of a dimethyl siloxane polymer (DMSP) (BY16-140, manufactured by Toray Silicone K.K.) at a high degree of polymerization having a plasticity of 1.40-1.90 which has been softened at a high temperature, through a side feeder, followed by cooling and cutting, thereby generating a polyacetal resin-based silicon gum concentrate.

Carbon Black:

BK-1: Carbon 35 (manufactured by Mitsubishi Kasei K.K.)

BK-2: Vulcan 9 (manufactured by Cabot K.K.)

20

#### b) Preparation of Resin Composition

10 kg of a polyacetal resin was melt kneaded with a polymer composition, a silicone gum concentrate and/or with or without carbon black, using a 35 mm twin screw extruder (DEM 35, manufactured by Toshiba K.K.), followed by water cooling and cutting to prepare resin compositions of this invention (samples 1-9) and comparative resin compositions (samples 11-19).

The composition of each pellet prepared is given in Table 1.

#### (2) Preparation of Molded Articles (Test Pieces) and Evaluation of Moldability.

Each pelletized product prepared in the above was injection molded out of the usual conditions to prepare test pieces for various tests.

Moldability was evaluated under the following basis in the molding of these test pieces by observing the surface appearance around the gate, with the rating results given in Table 1:

5      ⊙ : Excellent

O: Surface wrinkles were observed only in the vicinity around the gate.

Δ: Surface wrinkles were observed on a broader range around the gate.

X: Surface peels were observed.

10

### (3) Friction Characteristics Evaluation Test

#### a) Reciprocating Friction Wear Tester

15      The friction characteristics evaluation test was carried out using the reciprocating friction wear tester (developed by our company) illustrated in Figure 1. In Figure 1, the numbers on the drawing represent the following components:

- 20      1 - Balance Regulator
- 2 - Pressure Sensor
- 3 - Arm
- 4 - Load (M)
- 5 - Test Piece on the Reciprocating Table Side
- 6 - Test Piece on the Arm Side
- 25      7 - Motor
- 8 - Reciprocating Table A
- 9 - Computer
- 10 - Recorder

30      The reciprocating friction wear tester, as illustrated by Figure 1, is a Table (A) which reciprocates back and forth and an arm (B) which can be balanced by a weight. The reciprocating Table (A) on which a test piece is fixed is caused to reciprocate back and forth at a specific periodicity by a rotating disk connected to it. A triangular-shaped flat  
 35      test piece is secured on one end of the arm (B), on which a weight can be placed to adjust the load (M). As the reciprocating Table (A) starts its reciprocating motion and a test piece fixed on arm (B) slides over the test piece fixed on reciprocating Table (A), a pressure sensor incorporated

into the other end of arm (B) measures a frictional torque (Y) acting on the reciprocating motion which is then recorded on a recorder. This permits varying the load (M) to measure the change (YI) in frictional torque.

5

#### b) Coefficient of Dynamic Friction (u)

The reciprocating friction wear tester illustrated in Figure 1, explained by the above, was used to calculate the coefficient of dynamic friction (u) of each test piece according to Equation 1 which is then given in Table 1.

Load (M<sub>1</sub> - M<sub>5</sub>) : 0.5, 1.0, 1.5, 2.0, 3.0 kg  
 Reciprocating Length : 6.5 cm  
 15 Rotation Speed (Periodic Speed) : 4 rpm  
 Test Pieces:  
 The Arm Side : Triangular Flat Sheet 6.4 mm thick  
 Reciprocating Table Side : 3.2 mm-t x 18 mm x 100 mm

#### 20 Equation 1

$$\text{Coefficient of Dynamic Friction (u) = } (0.5 y_1 + 1.0 y_2 + \dots + 3.0 y_5)^2 / (0.5^2 + 1.0^2 + \dots + 3.0^2)$$

#### 25 c) Wear Rate ( W)

The reciprocating friction wear tester was used in a manner similar to the above to calculate the difference in the test piece weight before test (W<sub>0</sub>) and test piece (W<sub>1</sub>) measured after testing under the following conditions, thereby resulting in a wear rate ( W) (mg) which is given in Table 1:

35 Load (M) : 3.0 kg  
 Reciprocating Length : 7.5 cm  
 Rotary Speed (Periodical Speed) : 60 rpm  
 Number of Reciprocations : 10,000 cycles

## Test Pieces :

Arm Side: : Triangular Flat Sheet 6.4 mm  
thick

Reciprocating Table Side : 3.2 mm x 18 mm x 100 mm

5

(4) Heat Degradation Test (Resistance to Heat Aging and Grease  
Resistance)

10 A test piece was coated with a lithium based grease (tradename:  
Marutenptar 2 [Phonetic Translation], manufactured by Kydo Yushi  
K.K.) followed by holding for 188 hours in a 135°C oven and then  
carrying out the tensile test, thereby calculating percent retention with  
respect to the initial strength of each sample.

15 The resistance to heat aging and grease resistance were rated  
according to the following basis from the computer results of percent  
retention and were reported as grease resistance in Table 1.

20 O: % retention - 80% or greater  
X: % retention - less than 80%.

TABLE 1

Examples	Samples Nos.								
	1	2	3	4	5	6	7	8	9
Resin Composition (parts by wt.)									
Polyacetal resin	100	100	100	100	100	100	100	100	100
Polymer composition	A	A	A	B	D	A	A	A	B
Type									
Amount compounded	5.0	3.0	5.0	5.0	5.0	5.0	5.0	3.0	3.0
DMSP	1.0	1.0	2.0	2.0	1.0	1.0	1.0	2.0	1.0
Carbon Black	—	—	—	—	—	BK1	BK2	BK2	BK2
Friction Characteristics									
Coefficient of Friction ( $\mu$ )	0.07	0.08	0.05	0.06	0.06	0.07	0.07	0.05	0.07
Wear Rate ( $\Delta$ W:mg)	1.2	2.6	6.5	7.8	6.3	0.4	0.5	3.0	2.0
Moldability	○	⊙	○	○	⊙	⊙	⊙	⊙	⊙
Grease Resistance	○	○	○	○	○	○	○	○	○
Comparative Examples	11	12	13	14	15	16	17	18	19
Resin Composition (parts by wt.)									
Polyacetal resin	100	100	100	100	100	100	100	100	100
Polymer composition	—	—	A	A	A	A	C	—	C
Type									
Amount compounded	—	—	5.0	1.0	5.0	10.0	5.0	—	5.0
DMSP	—	2.0	—	1.0	3.0	1.0	1.0	—	2.0
Carbon Black	—	—	—	—	—	—	—	BK1	BK2
Friction Characteristics									
Coefficient of Friction ( $\mu$ )	0.39	0.04	0.22	0.08	0.03	0.15	0.08	0.34	0.05
Wear Rate ( $\Delta$ W:mg)	85.0	0.8	16.5	18.0	23.5	18.5	20.5	42.4	21.8
Moldability	⊙	×	△	○	×	×	○	⊙	△
Grease Resistance	×	×	○	×	×	×	○	×	○

The amount of DMSP (dimethyl siloxane polymer) was calculated from the amount of a silicone concentrate added. The amounts of carbon black added all were 0.3 parts by weight.

5 All of the samples of the examples containing both the polymer composition and dimethyl siloxane polymer within the defined ranges show good moldability, as well as excellent friction characteristics; in particular, each sample containing carbon black show further improved moldability and wear rate. On the other hand, the control examples  
10 which either contain none of the polymer compositions and dimethyl siloxane polymer or which may contain outside of the designated ranges, each fail to strike a balance in moldability and friction characteristics.

15 Samples containing a dimethyl siloxane polymer within the designated range each maintain the resistance to heat aging and grease resistance which are inherent characteristics of polyacetal resin compositions containing a polymer composition based on an olefinic polymer having glycidyl-group-containing pendent chains.

#### 20 Advantageous Effect of the Invention

The resin composition of this invention based on a polyacetal resin has extremely good moldability and gives molded articles which show excellent resistance to heat aging and grease resistance with no welded  
25 sections having reduced physical properties, along with considerably improved friction characteristics. These compositions are particularly suitable as molded articles and molding materials, particularly in switching mechanism parts where wear and squeaking are critical. The addition of a dimethyl siloxane polymer considerably improves friction  
30 characteristics, and the addition of carbon black further improves moldability and wear rates. These are extremely appropriate molded articles and molding materials when used in switching mechanism parts where wear and squeaking are critical.

## Claims

1. A polyacetal resin composition comprising per 100 parts by weight of a polyacetal resin, 2-7 parts by weight of a polymer  
5 composition based on an olefinic polymer having glycidyl-group-containing pendant chains and 0.5-2.5 parts by weight of a dimethyl siloxane polymer of a plasticity of at least one.
2. A resin composition as set forth in Claim 1 in which the  
10 polymer composition comprises a single olefin type polymer having glycidyl-group-containing pendent chains.
3. A resin composition as set forth in Claim 1 in which the  
polymer composition is a melt blend comprising 100 parts by weight of  
15 an olefinic polymer having glycidyl-containing pendent chains and 50-200 parts by weight of a styrene polymer containing oxazolyl groups.
4. A polyacetal resin-based resin composition further comprising  
100 parts by weight of a resin composition as set forth in any of the  
20 Claims 1 to 3 with 0.05-0.5 parts by weight of carbon black.
5. A molded article obtained by molding a polyacetal resin composition as set forth in any of Claims 1 to 4.



1/1




FIG. 1

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 96/03429

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08L59/00 //(C08L59/00,C08L83:04,C08L51:06),(C08L59/00,  
C08L83:04,23:08),(C08L59/00,C08L83:04,C08L51:06,C08L25:08),  
(C08L59/00,C08L83:04,C08L23:08,C08L25:08)

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,93 11206 (DU PONT) 10 June 1993 see claims 1-4 ---	
A	EP,A,0 290 230 (POLYPLASTICS CO) 9 November 1988 see claim 1 ---	
A	EP,A,0 420 564 (POLYPLASTICS CO) 3 April 1991 see claims 1-10 ---	
A	DOCUMENTATION ABSTRACTS JOURNAL A PLASTICS, POLYMERS., vol. 9240, 2 December 1992, LONDON GB, XP002006742 & JP,A,42 344 450 (DU PONT) 24 August 1992 -----	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \* "A" document defining the general state of the art which is not considered to be of particular relevance
- \* "E" earlier document but published on or after the international filing date
- \* "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \* "O" document referring to an oral disclosure, use, exhibition or other means
- \* "P" document published prior to the international filing date but later than the priority date claimed

- \* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* "&" document member of the same patent family

Date of the actual completion of the international search

26 June 1996

Date of mailing of the international search report

1 1. 07. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+ 31-70) 340-3016

Authorized officer

Stienon, P

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/03429

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9311206	10-06-93	CA-A- 2123981	10-06-93
		EP-A- 0613488	07-09-94
		JP-T- 7502768	23-03-95
		US-A- 5346737	13-09-94
-----			
EP-A-0290230	09-11-88	JP-A- 63277263	15-11-88
		JP-A- 63297453	05-12-88
		US-A- 4874807	17-10-89
		CA-A- 1316620	20-04-93
		US-A- 4879331	07-11-89
-----			
EP-A-0420564	03-04-91	JP-A- 3111446	13-05-91
		AT-T- 112583	15-10-94
		CA-A- 2026072	26-03-91
		CN-A,B 1051046	01-05-91
		DE-D- 69013110	10-11-94
		DE-T- 69013110	26-01-95
		ES-T- 2062396	16-12-94
		US-A- 5173532	22-12-92
-----			

**THIS PAGE BLANK (USPTO)**